

INTERNATIONAL STANDARD

IEC
61788-4

Second edition
2007-04

Superconductivity –

Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti composite superconductors



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

T

For price, see current catalogue

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definition.....	6
4 Requirements.....	7
5 Apparatus.....	7
5.1 Material of measuring mandrel or of measuring base plate.....	7
5.2 Diameter of the measuring mandrel and length of the measuring base plate.....	7
5.3 Cryostat for the resistance, R_2 , measurement	8
6 Specimen preparation.....	8
7 Data acquisition and analysis	8
7.1 Resistance (R_1) at room temperature	8
7.2 Resistance (R_2^*) just above the superconducting transition.....	8
7.3 Correction on measured R_2^* for bending strain.....	11
7.4 Residual resistance ratio (RRR)	11
8 Uncertainty and stability of the test method	11
8.1 Temperature.....	11
8.2 Voltage measurement.....	11
8.3 Current.....	11
8.4 Dimension	12
9 Test report.....	12
9.1 RRR value.....	12
9.2 Specimen	12
9.3 Test conditions.....	12
9.3.1 Report of test conditions.....	12
9.3.2 Report of R_1	13
9.3.3 Report of R_2	13
Annex A (informative) Additional information relating to the measurement of RRR	14
Annex B (informative) Statistical definitions	22
Figure 1 – Relationship between temperature and resistance	7
Figure 2 – Voltage versus temperature curves and definitions of each voltage.....	9
Figure A.1 – Bending strain dependency of RRR for pure Cu matrix of Nb-Ti composite superconductors (comparison between measured values and calculated values).....	15
Figure A.2 – Bending strain dependency of RRR for round Cu wires	15
Figure A.3 – Bending strain dependency of normalized RRR for round Cu wires.....	16
Figure A.4 – Bending strain dependency of RRR for rectangular Cu wires	16
Figure A.5 – Bending strain dependency of normalized RRR for rectangular Cu wires	17
Figure A.6 – Distribution of observed RRR of Cu/Nb-Ti composite superconductor	19
Figure A.7 – Definition of voltages	20

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –

**Part 4: Residual resistance ratio measurement –
Residual resistance ratio of Nb-Ti composite superconductors**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61788-4 has been prepared by IEC technical committee 90: Superconductivity.

This second edition cancels and replaces the first edition published in 2001. It constitutes a technical revision. The main revisions are the replacement of "accuracy" by "uncertainty" and a change in Figure 1, where the relationship between temperature and voltage is changed to the relationship between temperature and resistance.

The text of this standard is based on the following documents:

FDIS	Report on voting
90/203/FDIS	90/205/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

Copper is used as a matrix material in multifilamentary superconductors and works as an electrical shunt when the superconductivity is interrupted. It also contributes to recovery of the superconductivity by conducting heat generated in the superconductor to the surrounding coolant. The cryogenic-temperature resistivity of copper is an important quantity, which influences the stability of the superconductor. The residual resistance ratio is defined as a ratio of the resistance of the superconductor at room temperature to that just above the superconducting transition.

In this International Standard, the test method of residual resistance ratio of Nb-Ti composite superconductors is described. The curve method is employed for the measurement of the resistance just above the superconducting transition. Other methods are described in Clause A.4.

SUPERCONDUCTIVITY –

Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti composite superconductors

1 Scope

This part of IEC 61788 covers a test method for the determination of the residual resistance ratio (*RRR*) of a composite superconductor comprised of Nb-Ti filaments and Cu, Cu-Ni or Cu/Cu-Ni matrix. This method is intended for use with superconductors that have a monolithic structure with rectangular or round cross-section, *RRR* less than 350, and cross-sectional area less than 3 mm². All measurements are done without an applied magnetic field.

The method described in the body of this standard is the “reference” method and optional acquisition methods are outlined in Clause A.4.

2 Normative references

The following referenced document is indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815, *International Electrotechnical Vocabulary (IEV) – Part 815: Superconductivity*