

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS G 0556 : 2014

(JISF)

**Method of macro-streak-flaw test
for steel**

ICS 77.040.99

Reference number : **JIS G 0556 : 2014 (E)**

G 0556 : 2014

Date of Establishment: 1956-05-25

Date of Revision: 2014-03-20

Date of Public Notice in Official Gazette: 2014-03-20

Investigated by: Japanese Industrial Standards Committee
Standards Board
Technical Committee on Iron and Steel

JIS G 0556:2014, First English edition published in 2014-11

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

AT

PROTECTED BY COPYRIGHT

Contents

	Page
Introduction.....	1
1 Scope.....	1
2 Normative references	1
3 Terms and definitions	1
4 Classification of test methods.....	2
5 Step-down test method	2
5.1 Principle	2
5.2 Test piece	2
5.3 Tests	3
5.4 Method of determination	3
5.5 Indication	4
6 Blue fracture test method	7
7 Magnetic particle inspection method.....	7
8 Test report	7
Annex JA (normative) Blue fracture test method.....	8
Annex JB (normative) Magnetic particle inspection method	12
Annex JC (informative) Comparison table between JIS and corresponding International Standard	15

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by The Japan Iron and Steel Federation (JISF) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14.

Consequently, **JIS G 0556:1998** is replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Ministers and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Method of macro-streak-flaw test for steel

Introduction

This Japanese Industrial Standard has been prepared based on the first edition of **ISO 3763** published in 1976 with some modifications of the technical contents.

The portions with continuous sidelines or dotted underlines are the matters in which the contents of the corresponding International Standard have been modified. A list of modifications with the explanations is given in Annex JC.

1 Scope

This Standard specifies a step-down test method, blue fracture test method and magnetic particle inspection method to assess the non-metallic inclusions in rolled or forged steel with the naked eye or using a magnifying glass with a magnification of not more than $\times 10$.

NOTE : The International Standard corresponding to this Standard and the symbol of degree of correspondence are as follows:

ISO 3763:1976 *Wrought steels—Macroscopic methods for assessing the content of non-metallic inclusions* (MOD)

The symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are IDT (identical), MOD (modified), and NEQ (not equivalent) according to **ISO/IEC Guide 21-1**.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS B 0601 *Geometrical Product Specifications (GPS)—Surface texture: Profile method—Terms, definitions and surface texture parameters*

JIS G 0202 *Glossary of terms used in iron and steel (Testing)*

JIS G 0701 *Symbols of forming ratio for steel forging*

JIS Z 2320-1 *Non-destructive testing—Magnetic particle testing—Part 1: General principles*

JIS Z 8401 *Guide to the rounding of numbers*

3 Terms and definitions

For the purposes of this Standard, the terms and definitions given in **JIS G 0202** and the following apply.