

Australian Standard[®]

Printed board assemblies

**Part 1: Preparation, handling and
assembly**

This Australian Standard was prepared by Committee TE/6, Printed Circuits. It was approved on behalf of the Council of Standards Australia on 16 December 1988 and published on 13 October 1989.

The following interests are represented on Committee TE/6:

Australian Electrical and Electronic Manufacturers Association
Australian Tin Information Centre
Civil Aviation Authority
Confederation of Australian Industry
Department of Defence
Department of Industry, Technology and Commerce
Institution of Radio and Electronics Engineers, Australia
Telecom Australia

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 86200.

Australian Standard[®]

Printed board assemblies

**Part 1: Preparation, handling and
assembly**

First published as AS 3508.1—1989.

PREFACE

This Standard was prepared by the Organization's Committee on Printed Board Assemblies. During its preparation attention was given to BS 6221.20 *Printed Wiring Boards: Part 20—Guide for the assembly of printed wiring boards*, for which assistance due acknowledgment is given.

It covers handling of components, preparation of the base board, insertion of components, soldering, inspection and specialized subjects such as cleaning and conformal coating as part of a series of Standards on printed board assemblies.

Subjects such as assembly of surface mounted components are treated only briefly, as it is the subject of more recent treatment in Standards on various aspects of that subject and on surface mount land patterns based on preferred components. Also in course of preparation are Standards on cleanliness and applicable cleaning procedures; and the repair of printed circuits, which provide much greater detail than the brief items contained in this Standard.

Subjects which are covered in some detail include solder, soldering and solderability, all of which are inherent to the preparation of quality printed board assemblies. Attention is drawn to the discussion on solder and soldering methods of producing printed board assemblies. Solder flux and the properties of solder and soldering which require attention are also discussed.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 STORAGE	4
5 HANDLING OF COMPONENTS PRIOR TO ASSEMBLY	4
6 MOUNTING OF COMPONENTS	5
7 BOARD ASSEMBLY METHODS	7
8 SOLDERABILITY—PROCESS CONSIDERATIONS	8
9 SOLDERING	9
10 FLATNESS	11
11 ASSEMBLY OF SURFACE MOUNTED COMPONENTS	12
12 INSPECTION	12
13 CLEANING	14
14 CONFORMAL COATINGS	15
APPENDIX A. CONFORMAL COATINGS AND THEIR LIMITATIONS .	16

STANDARDS AUSTRALIA

Australian Standard
Printed board assemblies

Part 1: Preparation, handling and assembly

1 SCOPE. This Standard sets out guidelines and recommends principles and practices to be applied to the assembly of components on printed board assemblies irrespective of the method of manufacture of the printed board.

2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

AS

- | | |
|----------|--|
| 1057 | Quality assurance and quality control—Glossary of terms |
| 1099 | Basic environmental testing procedures for electrotechnology |
| 1099.2T | Part 2: Tests—Test T: Soldering |
| 1560 | Recommendations for the design and use of components intended for mounting on printed circuit boards |
| 1834 | Material for soldering |
| 1834.1 | Part 1: Solder alloys |
| 1834.2 | Part 2: Flux cored solders |
| 2508 | Safe storage and handling information cards for hazardous materials |
| 2546 | Printed boards |
| 2546.0 | Part 0: Terms and definitions |
| 2546.1 | Part 1: General requirements and test methods |
| 2546.3 | Part 3: Design and use |
| 2547 | Semi-conductor devices |
| 2547.1.1 | Part 1.1: Discrete devices—General |
| 3508 | Printed board assemblies |
| 3508.4 | Part 4: Acceptability of printed board and solder joints—Pictorial representation |

BS

- | | |
|------|--|
| 5917 | Specification for conformal coating material for use on printed circuit assemblies |
|------|--|

US Federal QQ-S-571—Solder, tin alloy: Tin-lead alloy; and Lead alloy Standard

3 DEFINITIONS.

For the purpose of this Standard the definitions given in AS 2546.0 and AS 1057 apply.

4 STORAGE.

4.1 Conditions. Components, printed boards and printed board assemblies should be stored in an area free from dust-generating surfaces and materials, and in a non-corrosive atmosphere to prevent deterioration.

To prevent or retard loss of solderability of boards or assemblies, the ambient temperature of dedicated storage areas should be within the range 15°C to 30°C, the relative humidity within the range 25% to 60%,

and as constant as possible. This may require the atmosphere to be conditioned for optimum results to be attained.

4.2 General. The use of sealed containers, including plastics bags, containing a desiccant is recommended. Bags or containers should not be contaminated by silicones, sulphur compounds or other detrimental residues.

Usage of printed board components, on a 'first in first out' basis should be strictly observed. Items which have been stored for periods in excess of their recommended storage life, should be tested for solderability before use.

Printed boards should be stored flat, either enclosed in bags as above or interleaved with suitable tissue paper, in suitable, well ventilated containers or racks. The extra precautions listed in Clause 5.2 as necessary for electrostatic-sensitive devices and assemblies containing such devices, should be stringently observed.

5 HANDLING OF COMPONENTS PRIOR TO ASSEMBLY.**5.1 General.**

5.1.1 Housekeeping. Work areas shall be maintained in a clean and orderly condition. All dirt, grease, flux, solder spatter, chips and other contaminating foreign material shall be promptly removed. Eating, smoking or drinking at the work-station shall not be permitted, and precautions shall be taken to preclude contamination by prohibiting products of such activities from the work area.

Surfaces of component leads and printed boards which are to be soldered shall not be handled with bare hands. If the part cannot be handled without touching the surface to be soldered, protective devices such as clean nylon or cotton gloves, finger cots, or special tooling shall be used.

5.1.2 Temperature and humidity. The temperature of the work area should be maintained at 24 ± 5 °C, and the relative humidity should not exceed 65%, in order to maintain acceptable moisture content.

5.1.3 Vapour control. Areas used for cleaning parts and assemblies where toxic vapours are generated shall employ a local exhaust system for removing the air contaminants.

5.2 Electrostatic sensitive devices.

5.2.1 General. It is recommended that safeguards should be taken with respect to semi-conductor components and devices against possible degradation or failure which can be caused by an electrostatic discharge.